

Adhesion			
-As Coated	ASTM D3359	Pass	5B (highest rating)
-Water Immersion	ASTM D870	Pass	65° C - 40 days
-Condensation Test	40 degrees C for 40 days	Pass	40 days
-Boiling Water	ASTM C373	Pass	5 Hours
-Humidity	DIN 50017	Pass	300 Hours
-Salt Spray	ASTM C1503-1	Pass	600 Hours
Chemical Resistance	ASTM C650	Pass	Acid and Alkali
Thin Set/Adhesive Mastic Compatibility	Adhesive applied to cured paint on glass subjected to one week wrapped with plastic at 40 deg. C and check for burn through. ALWAYS recommend use with mechanical fasteners	Suggested Products: Always use a mechanical fastener in addition to one of the approved adhesives from the technical data page of the Dreamwalls Color Glass website Use no acetone products.	
Pencil Hardness	ASTM D3363	Pass	2 H
Abrasion, Scratch Resistance			
-Hoffman Scratch	ASTM STP 500	Pass	1900g weight
Edge Chipping MEK Resistance Full Hide (White & Black)	QC Procedure QC Procedure Lenetta charts	No chipping evident 100+ double rubs Full hide at 25 microns	

*** Products should never be exposed to Exterior 1st surface exposure
All Pigments are Automotive Grade for excellent Fade Resistance.**

IMPORTANT: WHILE THE DESCRIPTIONS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH AND BELIEVED TO BE ACCURATE, IT IS PROVIDED FOR YOUR GUIDANCE ONLY. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE, WE RECOMMEND THAT YOU PERFORM AN ASSESSMENT TO DETERMINE THE SUITABILITY OF A PRODUCT FOR YOUR PARTICULAR PURPOSE PRIOR TO USE. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED, DATA OR INFORMATION SET FORTH. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, OR DATA PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. FURTHER, THE DESCRIPTIONS, DATA AND INFORMATION FURNISHED HEREUNDER ARE GIVEN GRATIS. NO OBLIGATION OR LIABILITY FOR THE DESCRIPTION, DATA AND INFORMATION GIVEN ARE ASSUMED. ALL SUCH BEING GIVEN AND ACCEPTED AT YOUR RISK.